

**AMENDMENTS TO THE CLAIMS**

1-10 (Cancelled)

11. (Currently amended) A fiber comprising starch, wherein the fiber has ~~a size ranging from about 0.02 dtex to about 5 dtex and a T<sub>g</sub> of at least about 30°C~~ an average fiber diameter of less than 10  $\mu$ m.
12. (Previously presented) The fiber according to Claim 11 wherein the fiber comprises from about 20% to about 99.99% by weight of the fiber of starch.
13. (Previously presented) The fiber according to Claim 11 wherein the fiber further comprises a plasticizer.
14. (Previously presented) The fiber according to Claim 13 wherein the plasticizer selected from the group consisting of: sorbitol, monosaccharides, disaccharides, glycerol, polyvinyl alcohol, polyethylene glycol and mixtures thereof.
15. (Previously presented) The fiber according to Claim 13 wherein the plasticizer is present in the fiber at a level of from about 5% to about 70% by weight of the fiber.
16. (Previously presented) The fiber according to Claim 11 wherein the fiber further comprises a cross-linking agent.
17. (Previously presented) The fiber according to Claim 16 wherein the cross-linking agent is selected from the group consisting of: polyamide-epichlorohydrin resins, urea-formaldehyde resins, glyoxylated polyacrylamide resins, melamine formaldehyde resins, polyethylenimine resins, dialdehyde starch resins and mixtures thereof.
18. (Previously presented) The fiber according to Claim 16 wherein the cross-linking agent is present in the fiber at a level of from about 0.1% to about 10% by weight of the fiber.
19. (Cancelled)
20. (Previously presented) A fibrous structure comprising a plurality of fibers, wherein at least one fiber is a fiber according to Claim 11.

21. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has an absorbency ranging from about  $1 \frac{\text{g}_{\text{Water}}}{\text{g}_{\text{Dry Structure}}}$  to about  $15 \frac{\text{g}_{\text{Water}}}{\text{g}_{\text{Dry Structure}}}$ .
22. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has a total flexibility ranging from about 1.0 g/cm to about 75 g/cm.
23. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has a geometric mean dry tensile strength ranging from about 10 g/cm to about 1200 g/cm.
24. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has an initial geometric mean wet tensile strength ranging from about 2 g/cm to about 400 g/cm.
25. (Previously presented) The fibrous structure according to Claim 24 wherein the fibrous structure has an initial geometric mean wet tensile strength ranging from about 2 g/cm to about 200 g/cm.
26. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has a geometric mean decayed wet tensile strength ranging from about 0 g/cm to about 20 g/cm.
27. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has a basis weight ranging from about 10 g/m<sup>2</sup> to about 450 g/m<sup>2</sup>.
28. (Previously presented) The fibrous structure according to Claim 20 wherein the fibrous structure has an apparent density ranging from about 0.04 g/cm<sup>3</sup> to about 0.12 g/cm<sup>3</sup>.
29. (Currently amended) A paper product comprising a fibrous structure, wherein the fibrous structure comprises a fiber comprising starch, wherein the fiber has ~~a size ranging from about 0.02 dtex to about 5 dtex and a Tg of at least about -30°C~~ an average fiber diameter of less than 10 μm.
30. (Currently amended) A fibrous structure comprising a fiber comprising starch, wherein the fiber ~~has a size ranging from about 0.02 dtex to about 5 dtex and a Tg of at least about -30°C~~ an average fiber diameter of less than 10 μm and wherein the fibrous structure has a basis weight ranging from about 10 g/m<sup>2</sup> to about 450 g/m<sup>2</sup>.
31. (New) The fiber according to Claim 11 wherein the fiber is a melt blown fiber.
32. (New) The fiber according to Claim 11 wherein the fiber is a spunbond fiber.

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**